

# Technical Data Sheet

## PREMIUM RUBBER WHITE WXM-300

### INTRODUCTION:

PREMIUM RUBBER WHITE WXM-300 (Extra Matt) is a kind of Special Acrylic Co-polymers Emulsion (water base) in which blended with Titanium Dioxide (TiO<sub>2</sub>) is flexhibits soft, durable film properties with excellent water and abrasion resistance. It is made to be applied for Pigment Preparation based and Pigment screen printing formulations and provide excellent adhesion for both natural and synthetic fibers (such as Knitting, Polyester, T/C, Cotton and so on). It is easy to obtain excellent fastness against normal after-treatment on fabrics (washing, chloride, enzyme etc.)

### CHARACTERISTICS:

1. Excellent hiding ability (Pigment shade will not be affected by the color of the base fabrics).
2. Short printing time and formulated to be suitable.
3. Excellent rubbing fastness, washing Fastness & water resistance
4. Excellent soft to hand-touch.
5. Excellent brightness results.

### CHEMICAL PROPERTIES:

APPEARANCE :White Paste

PH VALUE : 7±1

IONIC NATURE : Anionic

### RECIPES:

#### WHITE PRINT ON ANY DEEP GROUND:

PREMIUM RUBBER WHITE WXM-300	= 86%
PREMIUM RUBBER CLEAR CXM-301	= 10%
SILKFLEX ECO OXAL FIXER SU-400E	= 3%
AQUASOL FLOCK FIXER SF-103	= 1%
<hr/>	
PASTE FOR PRINTING	= 100%

#### WHITE PRINT ON ANY LIGHT GROUND:

PREMIUM RUBBER WHITE WXM-300	= 76%
PREMIUM RUBBER CLEAR CXM-301	= 20%
SILKFLEX ECO OXAL FIXER SU-400E	= 3%
AQUASOL FLOCK FIXER SF-103	= 1%
<hr/>	
PASTE FOR PRINTING	= 100%

**COLOR PRINT ON ANY LIGHT GROUND:**

PREMIUM RUBBER WHITE WXM-300 (Extra Matt)	= 31%
PREMIUM RUBBER CLEAR CXM-301(Extra Matt)	= 65%
SILKFLEX ECO OXAL FIXER SU-400E	= 3%
AQUASOL FLOCK FIXER SF-103	= 1%
<hr/>	
PASTE FOR PRINTING	= 100%

**COLOR PRINT ON ANY DEEP GROUND:**

PREMIUM RUBBER WHITE WXM-300 (Extra Matt)	= 51%
PREMIUM RUBBER CLEAR CXM-301(Extra Matt)	= 45%
SILKFLEX ECO OXAL FIXER SU-400E	= 3%
AQUASOL FLOCK FIXER SF-103	= 1%
<hr/>	
PASTE FOR PRINTING	= 100%

**APPLICATIONS:**

1. Please each printing has to get dried or cured, then proceed the next printing.
2. For fast drying after screen printing, curing in oven under 150°C~160°C, 2~3 mins.
3. The print can be dried at ambient temperature but allow for seven days before conducting wash test. Alternatively, these prints can be hot pressed at 120°C for 10 sec to help speed up the curing process.

**PRINTING PARAMETER:**

Fabric Type	: 100% Cotton
Mesh Count	: 86-230t/in (34-90 t/cm)
Mesh Tension	: 25-35 n/cm <sup>2</sup>
Squeegee	: 60-70 Durometer (Sharp/Square edge)
Curing	: 305°-320°F (150°-160°C) for 2 mint
Others Additives	: Fixer 3% by weight max
Storage	: 65°-90°F (18°-32°C), Avoid Direct Sun
Clean Up	: Water
Health & Safety	: As per MSDS

**COLOR LOADING:**

For Black Color	: 100% Clear
For Dark Colors	: 10% White & 90% Clear
For Medium Colors	: 20-30% White with 70-80% Clear
For Light Colors	: 50% White & 50% Clear
For Pastel Colors	: 90-100% White with 0-10% Clear

**NOTE:**

1. Well curing is very important to every printing .in case, any press and heat have to be done, make it on the next day at 100~140°C, 3~5 seconds by press& heat machine.

**CERTIFICATION:**

Free from **APEO** as per the requirements of Directive 2003/53/EC of the European Parliament and of the council 18<sup>th</sup> June 2003 amending for the 26<sup>th</sup> time Council Directive 76/769/EEC. Also free from **Cationic Surfactants**.

It is complied with the requirements of Directive 2002/61/EC of the European Parliament and of the council 19<sup>th</sup> July 2002 amending for the 19<sup>th</sup> time Council Directive 76/769/EEC regarding the restriction on the marketing & use of certain dangerous substances and preparation (**AZO** colorants)

The product does not contain any AZO aryl derivatives and one or more **AZO** groups (24 contains) banned amines mentioned in the German Consumer Goods Ordinance

The amount of heavy metal impurities (**Chromium, Mercury, Barium, Selenium, Antimony, Cadmium, Arsenic, Lead** etc.) present in all products are below the ETAD (Ecological and Toxicological Association of Dyes and Organic Pigments Manufacturers) recommended limit value guideline.

It complies with the **Oeko-Tex Standard 100**, which regard to the limit value of substance which are

Free of **carcinogenic dyestuffs, Flame Retardants, Perfluoro Compounds**

Free of **Formaldehyde, Chloroparaffins, Chromium VI (Cr<sup>6+</sup>)**

Free of harmful to health substance such as **pesticides, allergy-inducing dyestuff or tin-organic compounds** etc

The product satisfies the requirements that are defined in Article 57 of regulation EC no 1907/2006 (The **REACH** Regulation). Also there is no substance from the **SVHC** "candidate list"

Compliant with CPSIA 2008 (Consumer Product Safety Improvement Act) Section 101, Lead Content in Substrates (<300 ppm lead); 16 CFR, Part 1303, Lead in Paint (<90 ppm lead); and CPSIA 2008, Section 108, Phthalates (<.1% **DEHP, DBP, BBP, DINP, DIDP, DNOP**).

It also free from **Chlorinated Aromatic Hydrocarbon, Phenols (PCP, TeCP, OPP) and Others restricted Organic Compound (DBT, DOT, TBT, TOT, TCyHT, TPT, TPhT), PCB, PCT, PVC & Triclosan**